

Purolite™ UltraClean™ UCW9966

Poliestireno Gel, Gel, Resina mixta,
Forma de hidrógeno, Forma
hidróxido, No separables, Grado de
Agua ultrapura

PRINCIPALES APLICACIONES

- Agua ultrapura

APROBACIONES REGULADORAS

- Certificado Halal IFANCA

ENVASE TÍPICO

- Caja de 1 pie³
- Tambor (plástico) de 50 L
- Tambor (fibra) de 5 pie³

CARACTERÍSTICAS FÍSICAS Y QUÍMICAS:

Aspecto	Esferas	
TOC (max.)	< 1 ppb TOC después de 100 BV de enjuague a 30 BV/h (*)	
Resistividad	> 18 MΩ después de 2 BV de enjuague a 30 BV/h (*)	
Peso de envío (aprox.)	670 - 710 g/L (41.9 - 44.4 lb/pie ³)	
Límite de temperatura	60 °C (140.0 °F)	
Nombre del componente	Aniónica Tipo Gel Ultra limpia	Aniónica Tipo I Gel UltraClean
Estructura del polímero	Gel reticulado poliestireno con divinilbenceno	Gel reticulado poliestireno con divinilbenceno
Grupo funcional	ácido sulfónico	Amonio cuaternario de tipo I
Forma iónica	forma H ⁺	OH ⁻ forma
Catión / anión relación química equivalente	1	1
Capacidad total (min.)	1.9 EQ/L (forma H ⁺)	1.0 EQ/L (OH- forma)
Conversión (min.)	99.9 % (forma H ⁺)	95 % (OH- forma)
Retención de la humedad	49 - 54 % (forma H ⁺)	52 - 58 % (Cl ⁻ forma)
Nota de pie de página	* Calidad del agua de entrada para lavado: > 17.5 M Ω cm; < 2 ppb TOC	

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puoliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puoliteresins.com or complete a Contact Us form via PuoliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.