

Purolite™ CriticalResin™ NRW5070XLC

Polistirenica Macroporosa, Resina anionica forte di Tipo I, Forma idrossido, Alta porosità, bassissimo contenuto di cloruri, Grado nucleare

PRINCIPALI APPLICAZIONI

- Sovrastrato anionico
- Polishing refrigerante primario
- Refrigerante ad alti livelli di boro e litio

VANTAGGI

- Eccellente stabilità fisica e chimica
- Minimo rilascio di cloruri
- Rimozione di colloidii molto fini
- Alta capacità operativa

* Shelf life di 12 mesi

SISTEMI

- Letto online per CVCS

IMBALLI TIPICI

- Scatola da 1 CF
- Fusto da 5 CF (in fibra)

CARATTERISTICHE CHIMICHE E FISICHE TIPICHE:

Struttura del Polimero	Polistirene macroporoso reticolato con divinilbenzene
Aspetto	Perle sferiche opache
Gruppo Funzionale	Ammonio quaternario di tipo I
Forma Ionica	forma OH-
Capacità totale (min.)	1 eq/L (21.8 Kgr/ft³) (forma OH-)
Umidità	50 - 55 % (forma Cl ⁻)
Distribuzione granulometrica	425 - 1200 µm
< 425 µm (max.)	2 %
Coefficiente di uniformità (max.)	1.7
Conversione (min.)	95 % (forma OH-)
Forma anionica, CO ₃ ²⁻ (max.)	5 %
Forma anionica, SO ₄ ²⁻ (max.)	0.2 %
Forma anionica, Cl ⁻ (max.)	0.05 %
Impurezze di Ferro (max.)	100 ppm
Impurezze di Sodio (max.)	25 ppm
Impurezze di Metalli Pesanti (max.)	50 ppm
Limite di temperatura, letto non rigenerabile	100 °C (212.0 °F) (forma OH-)
Limite di temperatura, letto rigenerabile	60 °C (140.0 °F) (forma OH-)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puoliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puoliteresins.com or complete a Contact Us form via PuoliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.