

# Purolite™ S108

Polistirenica Macroporosa, Resina chelante N-metilglucamina, Grado acqua potabile

## PRINCIPALI APPLICAZIONI

- Rimozione del boro
- Rimozione del boro - Acqua potabile
- Boron Removal - Waste Water

## VANTAGGI

- Eccellenti cinetiche

## CERTIFICAZIONI

- Certificato OK Kosher
- Certificato Halal LPPOM MUI
- Certificato IFANCA Halal
- Certificato da WQA secondo lo standard NSF/ANSI 61
- Approvato secondo il Water Regulations Advisory Scheme

## IMBALLI TIPICI

- Sacco da 1 CF
- Sacco da 25 litri
- Fusto da 5 CF (in fibra)
- Saccone da 1 m3
- Saccone da 42 CF

## CARATTERISTICHE CHIMICHE E FISICHE TIPICHE:

Struttura del Polimero	Polistirene macroporoso reticolato con divinilbenzene
Aspetto	Perle sferiche
Gruppo Funzionale	N-metilglucamina
Forma Ionica	forma FB
Capacità totale (min.)	0.6 eq/L (13.1 Kgr/ft³) (forma FB )
Umidità	60 - 66 % (forma Cl <sup>-</sup> )
Distribuzione granulometrica	425 - 630 µm
< 425 µm (max.)	5 %
Coefficiente di uniformità (max.)	1.2
Rigonfiamento reversibile, BL → Cl <sup>-</sup> (max.)	25 %
Densità	1.1
Peso di spedizione (approx.)	670 - 730 g/L (41.9 - 45.6 lb/ft³)
Limite di temperatura	60 °C (140.0 °F)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.


[www.puoliteresins.com](http://www.puoliteresins.com)



We're ready to solve your process challenges.

For further information on products and services, visit [www.puoliteresins.com](http://www.puoliteresins.com) or complete a Contact Us form via [PuoliteResins.com/contact-us](http://PuoliteResins.com/contact-us) or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

