

# Purolite™ CriticalResin™ NRW1160Li7

polistyrenowy żelowy, żywica kationitowa silnie kwaśna, forma litowa 7, jednorodny zakres uziarnienia, uziarnienie do aplikacji nuklearnych

## GŁÓWNE ZASTOSOWANIA

- kontrola pH - obieg chłodzący reaktor

## ZALETY

- wysoka pojemność robocza
- wysoki stopień konwersji do formy litowej-7

## SYSTEMY

- wstępne chłodzenie

## DOSTĘPNOŚĆ OPAKOWAŃ

- karton 1 CF
- beczka (kartonowa) 6 ft³

## PODSTAWOWE WŁAŚCIWOŚCI FIZYCZNE I CHEMICZNE:

Struktura polimeru	żelowy polistyren sieciowany dwuwinylobenzenem
Wygląd	kuliste ziarna
Grupy funkcyjne	kwasy sulfonowe
Forma jonowa	forma $Li^+$
całkowita pojemność (min.)	2.4 val/L (52.4 Kg/ft132) (forma $Li^+$ )
zawartość wilgoci	30 - 40 % (forma $Li^+$ )
główna średnica	625 ± 75 µm
współczynnik jednorodności (max.)	1.2
konwersja (min.)	99.9 % (forma $Li^+$ )
zanieczyszczenie żelazem (max.)	50 ppm
zanieczyszczenie sodem(max.)	40 ppm
zanieczyszczenie metalami ciężkimi (max.)	40 ppm
ciężar właściwy	1.26
ciężar nasypowy (średnio)	790 - 830 g/L (49.4 - 51.9 lb/ft132)
limit temperatury	120 °C (248.0 °F)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

[www.puroliteresins.com](http://www.puroliteresins.com)



We're ready to solve your process challenges.

For further information on products and services, visit [www.puroliteresins.com](http://www.puroliteresins.com) or complete a Contact Us form via [PuroliteResins.com/contact-us](http://PuroliteResins.com/contact-us) or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.