

Purolite™ CriticalResin™ NRW3560XLCLi7

polistirenic macroporos, Gel, Cationit /anionit puternic bazic, Forma Litiu 7: hidroxid, Pat mixt în raport de echivalenți 1:1, Coninut scăzut de clor, Categoria (de rasini tip) nuclear

PRINCIPALELE APLICATII

- Purificarea agentului de răcire principal
- agent de răcire cu coninut ridicat de bor i litiu

AVANTAJE

- stabilitate fizică i chimică excelentă
- eliberare minimă de clor
- Grad ridicat de conversie în forma Litiu7 & forma hidroxid
- Extractibile organice reduse si lavabile
- Capacitate ridicată de operare

* perioada de valabilitate de 12 luni

SISTEME

- CVCS pat online

AMBALAJE TIPICE

- Cutie de 1 CF
- Butoi (Fibră) de 5 CF

CARACTERISTICI TIPICE FIZICE SI CHIMICE

Aspect	Perle sferice	
Distribuia granulometrică	425 - 1200 µm	
< 425 µm (max.)	2 %	
coeficient de uniformitate (max.)	1.7	
Impurități de fier (max.)	50 ppm	
Impurități de sodiu (max.)	30 ppm	
Impurități de metale grele (max.)	40 ppm	
Greutate de transport (aprox.)	720 - 750 g/L (45.0 - 46.9 lb/ft³)	
Limita de temperatură, pat neregenerabil	100 °C (212.0 °F)	
Limita de temperatură, pat regenerabil	60 °C (140.0 °F)	
nume component	Cationit puternic acid de tip macroporos Li7	Anionit Puternic Bazic de tip gel
structura polimerului	polimer polistiren macroporos reticulat cu DVB	Copolimer gel polistirenic reticulat cu divinilbenzen
grupare functionala	acid sulfonic	Grupari quaternare de amoniu tip I
Formă ionică	forma Li^+	forma OH^-
raportul echivalent cationit/anionit	1	1
Capacitate totală (min.)	2.1 eq/L (forma Li^+)	1.1 eq/L (forma OH^-)
conversie (min.)	99.9 % (forma Li^+)	95 % (forma OH^-)
formă anionică, CO^- (max.)	5 %	
formă anionică, SO_4^{2-} (max.)	0.1 %	


formă anionică, Cl ₃ ²⁻ (max.)	0.05 %	
densitate specifică	1.24	1.08

Caracteristici hidraulice

PRESSURE DROP

The pressure drop across a bed of ion exchange resin depends on the particle size distribution, bed depth, and voids volume of the exchange material, as well as on the flow rate and viscosity of the influent solution. Factors affecting any of these parameters—such as the presence of particulate matter filtered out by the bed, abnormal compressibility of the resin, or the incomplete classification of the bed—will have an adverse effect, and result in an increased head loss. Depending on the quality of the influent water, the application and the design of the plant, service flow rates may vary from 10 to 40 BV/h.

PRESSURE DROP ACROSS RESIN BED



Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.


www.puoliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puoliteresins.com or complete a Contact Us form via PuoliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.