

ОПИСАНИЕ ПРОДУКТА

Purolite™ - Пьюролайт C107E

Полиакриловая Пористая,
Слабокислотная катионообменная
смола, Водородная форма, Класс
для питьевой воды

ОСНОВНЫЕ НАЗНАЧЕНИЯ

- Умягчение - Питьевая вода
- Удаление щелочности

ПРЕИМУЩЕСТВА

- Исключительная кинетика
- Высокая Рабочая Емкость
- Исключительная селективность по тяжелым металлам

СИСТЕМЫ

- Водно-органические растворы

РАЗРЕШАЮЩАЯ ДОКУМЕНТАЦИЯ

- Сертифицировано Ассоциацией Контроля качества воды по стандарту 61 NSF ANSI
- Одобрено WRAS Великобритании

ТИПОВАЯ УПАКОВКА

- Мешок объемом 1 кубический фут
- Мешок (куль) объемом 25 литров
- Цилиндрическая бочка (волоконная) объемом 5 кубических футов
- Большой мешок (куль) объемом 1 м3
- Большой мешок объемом 42 кубических фута

ТИПОВЫЕ ФИЗИЧЕСКИЕ И ХИМИЧЕСКИЕ ХАРАКТЕРИСТИКИ

Структура полимера	Пористая сшитая полиакриловая кислота
Внешний вид	Сферические зерна
Функциональная группа	Карбоксильная кислота
Ионная форма	H ⁺ форма
Полная обменная емкость (не менее)	3.6 г-экв/л (78.7 Килогран/куб.фут) (H ⁺ форма)
Остаточная влажность	53 - 58 % (H ⁺ форма)
Диапазон размеров частиц	300 - 1600 мкм
< 300 мкм (не более)	0.5 %
Обратимое набухание при переходе H ⁺ → Ca ²⁺ (не более)	25 %
Обратимое набухание при переходе H ⁺ → Na ⁺ (не более)	90 %
Удельный вес	1.17
Насыпной вес (приблизительно)	735 - 770 г/л (45.9 - 48.1 фунт/куб.фут)
Максимальная рабочая температура	120 °C (248.0 °F)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puroliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puroliteresins.com or complete a Contact Us form via PuroliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

