

# Purolite™ C150TL

聚苯乙烯 大孔, 强酸阳离子树脂, 钠型, 三层混床系统

## 主要应用

- 脱盐

## 产品优势

- 优良的抗渗透和热冲击能力
- 优良的动力学性能

## 适用系统

- 三层床系统

## 包装样式

- 1 CF 编织袋
- 25L 阀口袋
- 5 CF 纤维板桶
- 1M3 立方袋
- 42 ft³ 立方袋

## 典型物理和化学参数

聚合物骨架	大孔型聚苯乙烯二乙烯苯交联
外观	球状颗粒
官能团	磺酸
离子型态	Na <sup>+</sup> 型
全交换容量 ( 最小 )	1.8 eq/L (39.3 Kgr/ft <sup>3</sup> ) (Na <sup>+</sup> 型)
含水量	48 - 53 % (Na <sup>+</sup> 型)
粒径分布	710 - 1200 μm
< 710 μm (最大)	1 %
均一系数 ( 最大 )	1.3
转型膨胀率, Na <sup>+</sup> → H <sup>+</sup> ( 最大 )	7 %
比重	1.25
包装密度 ( 大约 )	775 - 800 g/L (48.4 - 50.0 lb/ft <sup>3</sup> )
温度限制	120 °C (248.0 °F) (H+ 型)
温度限制	140 °C (284.0 °F) (Na <sup>+</sup> 型)

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.


[www.puroliteresins.com](http://www.puroliteresins.com)



We're ready to solve your process challenges.

For further information on products and services, visit [www.puroliteresins.com](http://www.puroliteresins.com) or complete a Contact Us form via [PuroliteResins.com/contact-us](http://PuroliteResins.com/contact-us) or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

